

**DESCRIPTION**Name: **Soak-Off Methacrylate Resin****TYPICAL PHYSICAL AND CHEMICAL PROPERTIES**

PROPERTY	RESULT
Appearance at Room Temperature	Clear liquid
Molecular Formula	$C_{88}H_{162}N_4O_{24}$
Molecular Weight	1660.24
Viscosity @ 25°C	86,000 cps
TGA Weight Loss @ 100°C	0.26
CAS Registration Number	Not Registered
Recommended Storage Temp	5°C

*Data is for reference only and may vary depending on testing method used. The structure shown above is an idealized representation of a statistical distribution.*

**RECOMMENDED FORMULATION USE:**

**H1318** is recommended for cosmetic nail gels. This material is also a 3-D printing resin candidate.

**CONTACT:****REQUEST A SAMPLE OR PLACE AN ORDER**

Customer Support

☎ 858-348-1122

✉ [info@dmhpi.com](mailto:info@dmhpi.com)

REF: DMHPI Part Number: H1318